

SA Base

SELF-ADHERED SBS MODIFIED BITUMINOUS BASE SHEET



TopShield® SA Base Sheet is a premium, SBS modified, glass fiber reinforced, self-adhesive modified bituminous base sheet for use in most low slope and steep slope roof system applications. TopShield® SA Base is a perfect alternative to the application of roofing using conventional application methods of torching, hot asphalt mopping, or using cold applied adhesives.

FEATURES AND BENEFITS

- Multiple uses as base sheet for self-adhered, torched, hot mopped and cold applied applications.
- No specific tools required. Clean, easy to handle, peel and stick self-adhering application.
- No fumes during application, eliminating odors caused by adhesives and hot asphalt.
- 30-40% quicker installation than conventional application
- Ultraviolet resistant polyolefinic film surface
- Glass fiber reinforcement ensures exceptional dimensional stability
- ASTM standard – ASTM D4601
- Meets and/or exceeds the applicable sections of ASTM D 6163 and ASTM D 1970 specifications
- 30 day exposure limit
- Miami Dade County approved
- ICC approved
- IFlorida Building Code approved
- Product qualified for use as a component of a FORTIFIED Roof™
- Texas Department of Insurance approved
- UL Classified (R 13228) for use in Class A and B roofs
- 10, 15, 20 and 25 Year Limited Warranties

USAGE

- TopShield® SA Base is designed as base sheet for self-adhering membrane systems. SA Base is also an ideal base sheet for torch, hot mop and cold applied conventional applications.

PRODUCT DATA

Width	36 in
Length	72 ft
Thickness	54 mil (nominal)
Gross Coverage	216 sq ft
Weight	66 lb (nominal)

GENERAL PRECAUTIONS

- Install SA Base only when material interface temperatures (air, deck, material) are 40° F and rising.
- Do not install when any form of moisture such as water, ice, snow, dew, rain, etc. is present.
- Ensure roof has proper slope and drainage prior to installation. The roof must meet the TopShield® minimum slope requirements.
- Proper ventilation is critical. When applying over the entire roof deck, the roofing system must provide sufficient ventilation, including both ridge and soffit venting.
- A full, irreversible adhesion is achieved when the membrane goes through a complete heat cycle. Do not attempt to remove the membrane immediately after adhesion to the substrate.
- Use of a hand-held "hot air gun" might help in enhancing adhesion during application of membrane in cooler weather.
- SA Base must be covered with a finished roof covering within the specified exposure time of the product. Refer to section on Features and Benefits for exposure time.

STORAGE

- SA Base rolls must be stored indoors, in a dry location.
- Boxes must be stored on end only. Do not store in a leaning position.
- The rolls must be protected from the elements. Do not expose rolls to direct sunlight.
- Store rolls at room temperatures. Prolonged exposure to elevated temperatures may reduce the adhesive characteristics of the membrane.

SURFACE PREPARATION

- Surface must be clean, dry, and without voids that may interfere with adhesion.
- For re-roofing, all old roofing and other loose materials must be removed prior to installation.
- Acceptable substrates for adhesion of TopShield® membranes can be found at the TopShield® Products website.
- For best results, surface may be primed with an ASTM D 41 Primer prior to installation of SA Base. When primer is used, ensure the primer is fully dry prior to application of SA Base.
- If SA Base is left exposed for more than 30 days, the SA Base surface must be primed prior to installation of a self-adhesive membrane.

PROPERTIES

PROPERTY	TYPICAL VALUES	REF TEST
Max. Load @ 0° F, MD & XMD	75 lbf/in.	ASTM D5147
Elongation @ 0° F, MD & XMD	2%	ASTM D5147
Max. Load @ 73.4° F, MD & XMD	35 lbf/in.	ASTM D5147
Elongation @ 73.4° F, MD & XMD	10%	ASTM D5147
Tear Strength @ 73.4° F	35 lbf	ASTM D5147
Low Temperature Flexibility	0°F	ASTM D5147
Dimensional Stability	0.5% max.	ASTM D5147
Compound Stability @ 215° F	Pass	ASTM D5147
Adhesion to Plywood @ 40° F	2 lbs/ft. of width	ASTM D1970
Adhesion to Plywood @ 75° F	20 lbs/ft. of width	ASTM D1970




APPLICATION

- Cut the SA Base roll to suitable, manageable lengths before installation.
- Position the pre-cut SA Base beginning at the lowest corner of the roof where the eave (gutter edge) and rake (rising edge) intersect.
- Align SA Base so that it is parallel with the edge of the eave and extend over the eave and rake approximately 3/8".
- Starting at the middle and extending to one end of SA Base, drive securing nails in 18" centers in the side lap area, 1 1/2" from the edge. Do not drive the nails all the way in.
- Backroll the unsecured portion of the roll up the middle where the first securing nail is driven.
- Apply a 1/16" thick layer of asphalt plastic cement over the eave and rake metal drip edges extending 2" to 3" onto the deck surface where the roll will intersect.
- Carefully remove the release film the full width of the sheet and apply the SA Base membrane firmly into place as it is being applied, taking care to avoid wrinkling or creasing of the roll.
- Remove the securing nails from the other half of SA Base, backroll and apply in like manner.
- On slopes greater than 2:12, drive nails flush in the selvage area 1 1/2" from the edge on 18" centers, after SA Base has been applied and prior to the next overlapping course.
- Apply the next eave course in the same manner overlapping the first course at the end lap by 6".
- Apply full roll width, a 1/16" thick layer of asphalt plastic cement to the surface of the first course in the 6" end lap area before adhering the next course.
- Lap the succeeding course over the side lap for minimum 3".
- Apply succeeding courses in like manner, as in steps above.
- Stagger the end laps a minimum 3' from the preceding course.
- At the T-joint (where an end lap and next overlapping course intersect), apply a bead of asphalt plastic cement before the overlapping course is laid.
- Roll the entire membrane surface, paying special attention to side laps, end laps and T-joints. Roller weight shall be 70 lb. minimum for low slope (<2:12 pitch) and 28 lb. minimum for steep slope (>2:12 pitch).

WARRANTY

TopShield® SA Base is warranted to be free from manufacturer's defects.

NOTE: All statements, information and data, given herein are believed to be accurate and reliable, but are presented without guaranty, warranty or responsibility of any kind, expressed or implied, except as may be indicated otherwise in this literature.



Scan QR Code for additional information.